

TEST REPORT

DATE: 09-11-2018 TEST NUMBER: 0250291

CLIENT	Egetgepper a/s
	290,40000 473

	AATCC 165 Colorfastness to Crocking - Textile Floor Coverings
TEST METHOD CONDUCTED	(AATCC Crockmeter Method)



DESCRIPTION OF TEST SAMPLE		
IDENTIFICATION	Una Mineral ECT350	
CONSTRUCTION	Loop Pile	
BACKING	Attached Cushion	

GENERAL PRINCIPLE

This method is designed to determine the degree of color which may be transferred from the surface of colored textile material to other surfaces by rubbing. Color transferred to the white test cloth is assessed by comparison with the AATCC Chromatic Transference Scale.

TEST RESULTS

	Wet	Dry	
	Crock	Crock	
COLOR/IDENTIFICATION	Rating	Rating	C
Una Mineral ECT350	5.0	5.0	

	Wet	Dry
	Crock	Crock
COLOR/IDENTIFICATION	Rating	Rating

AATCC RATING KEY			
5	No change		
4	Slight change		
3	Noticeable change		
2	Considerable change		
1	Severe change		

APPROVED BY:

NVLAP

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the producttested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples testedand is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc. shall not be used under any circumstance in advertising to the general public.



714 Glenwood Place Dalton, GA 30721 706-226-3283 Fax: 706-226-6787 protest@optilink.us