

ege testcertificate

Herning 2024-04-19

Subject:	Classification
Reference No.:	B-3296
Reference:	Grand CF
Dimension:	Rug
Description of sample:	Tuftet loop pile 100 % wool Floor covering with pile Felt Backing
Testing atmosphere	Unless otherwise specified the sample has been conditioned and tested, where appropriate, in the standard atmosphere for conditioning and testing textiles EN ISO 139:2005 of 65 ± 4 % R.H. and 20 ± 2 °C.

Testmethod	Testresults	Requirements
Total mass (g/m²) ISO 8543	3555	
Total thickness (mm) ISO 1765	17,37	
Thickness of pile above substrate (mm) ISO 1766	13,2	
Mass of pile above substrate per unit area (g/m²)	1477	
Surface pile density (g/cm³) ISO 8543	0,112	
Number of tufts or loops (per dm²)	19.741	
Vettermann ISO 10361 Short turn Long turn	Note 3 Note 2	
Fiber bind ≥80% natural fibres ISO/PAS 11856 at 30.000 rubs 10.000 rubs 10.000-30.000 rubs	90 mg 0,0018 mg pr rub	<250 mg <0,0035 g per rub
Basic requirements	Fulfilled	
Use Class	Class 22	

The information contained on page no 1-2 of this certificate is hereby certified to be correct statement of the tests and investigations carried out by ege testlaboratory on the material referred to.

Signed By



Lene M Weissenborn
Laboratory Technician

Reported By



Villads Chester
Global Quality Manager