

ege testcertificate

Herning 30.08.2023

Subject:	Classification
Reference No.:	HC-3244
Reference:	Graphic wool 1600 LF
Dimension:	Roll
Description of sample:	Tuftet cut pile 100 % Wool Felt Backing
Testing atmosphere	Unless otherwise specified the sample has been conditioned and tested, where appropriate, in the standard atmosphere for conditioning and testing textiles EN ISO 139:2005 of 65 ± 4 % R.H. and 20 ± 2 °C.

Testmethod	Testresults	Requirements
Total mass ISO 8543	2664 g/m ²	
Total thickness ISO 1765	12,2 mm	
Thickness of pile above substrate (mm) ISO 1766	7,0 mm	
Mass of pile above substrate per unit area (g/m²)	1007 g/m ²	
Surface pile density (g/cm³) ISO 8543	0,125 g/cm ³	
Number of tufts or loops (per m²)	149.000 tufts/m ²	
Vettermann ISO 10361 Short turn Long turn	Note 4 Note 3	See EN1307
Suitable for use on stairs EN ISO 12951 Test B	Suitable for intensive use 18,7 N	 Min. 15 N
Body voltage ISO 6356	1,7 kV	≤ 2 kV
Basic requirements	Fulfilled	
Use Class	Class 33	

The information contained on page no 1-2 of this certificate is hereby certified to be correct statement of the tests and investigations carried out by ege testlaboratory on the material referred to.

Signed by



Dorthe Daa Pedersen
Laboratory Technician

Reported By



Henrik Schmidt Hansen
Quality & Environmental Director