

TEST REPORT

DATE: 03-04-2019

Page 1 of 1

TEST NUMBER: 0254590

CLIENT	Egetaepper a/s
--------	----------------

TEST METHOD CONDUCTED	AATCC 16 Colorfastness to Light (Option 3)
-----------------------	--



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Highline Loop
BACKING	Woven Synthetic

GENERAL PRINCIPLE

This test specimen is exposed to a predetermined amount of radiant energy under specified conditions of temperature and relative humidity. The lightfastness of the specimen is assessed by comparing the exposed and the unexposed portions of the test sample with the AATCC Gray Scale for Evaluating Color Change.

TEST RESULTS

EXPOSURE	40 AFU
----------	--------

COLOR	RATING
Highline Loop	3.5

IDENTIFICATION	RATING

IDENTIFICATION	RATING

AATCC RATING KEY	
5	No change
4	Slight change
3	Noticeable change
2	Considerable change
1	Severe change

APPROVED BY: _____

Gary Asberry



This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc., shall not be used under any circumstance in advertising to the general public.



PJLA TESTING LAB CODE 93341

744 Glenwood Blvd

Dallas, GA 30324

760 226 2222

Fax: 760 226 2727

www.pjla.com