

## ege testcertificate

<b>Subject:</b>	<b>Light Reflectance</b>
<b>Reference No.:</b>	1316
<b>Reference:</b>	Highline Carré
<b>Description of sample:</b>	Tuftet carpet, loop pile Colour palettes 5500 Colour Scale 1-12 5520 Colour Scale 1-12 5575 Colour Scale 1-12 5595 Colour Scale 1-12
<b>Testing atmosphere</b>	Unless otherwise specified the sample has been conditioned and tested, where appropriate, in the standard atmosphere for conditioning and testing textiles EN ISO 139:2005 of $65 \pm 4$ % R.H. and $20 \pm 2$ °C.

### Background

LRV is an instrumental measurement made using a spectrophotometer.

It is equivalent to CIE Y and is the proportion of visible light reflected by a surface, weighted for the sensitivity to light of the human eye.

LRV is expressed on a scale of 0-100 where absolute white has a value of 100 and absolute black has a value of 0. In practice white may be about 85 and black about 6.

For people with adequate vision, difference in hue or chroma (colour intensity), provide sufficient visual contrast. But for people who are visually impaired the main feature of a surface which determines the ability to identify differences in colour is the amount of light the surface reflects, or it's LRV.

### Test procedure

The light reflectance value for the sample was determined using a Chroma Meter reflectance spectrophotometer with a large area CR-410 measuring head.

The sample was subjected to measurements and viewed at 0° with illuminant C. The light reflectance was determined using CIE Y, according to BS 8493:2008.

**ege**<sup>®</sup>

we create more than carpets

egetæpper a/s  
Industrivej Nord 25  
Postbox 190  
DK-7400 Herning

Tel: +45 97 11 88 11  
Fax: +45 97 11 95 80

ege@ege.dk  
www.egecarpet.com

CVR 38 45 42 18

**Test results CIE Y :**

Colour no.	Colour palette 5500	Colour no.	Colour palette 5520	Colour no.	Colour palette 5575	Colour no.	Colour palette 5595
gb1 - K40501	18,92	gb1 - A20041	47,19	gb1 - K28328	42,09	gb1 - K28601	26,77
gb2 - K40502	2,63	gb2 - A20042	31,67	gb2 - K28329	29,30	gb2 - K28602	16,17
gb3 - K40503	14,37	gb3 - A20043	19,23	gb3 - K28378	18,66	gb3 - K28603	9,46
gb4 - K40504	38,30	gb4 - K20044	9,82	gb4 - K28374	9,28	gb4 - K20012	2,86
gb5 - K40505	4,34	gb5 - K20045	4,82	gb5 - K28366	4,06	gb5 - H28605	3,02
gb6 - K40506	5,38	gb6 - K20046	14,81	gb6 - K28364	7,86	gb6 - K28606	5,80
gb7 - K40507	4,86	gb7 - K20047	7,16	gb7 - K28380	19,15	gb7 - K28607	6,48
gb8 - K40508	13,96	gb8 - K20048	19,00	gb8 - K28379	28,23	gb8 - K28608	15,97
gb9 - K40509	5,28	gb9 - K20049	9,39	gb9 - K27886	21,21	gb9 - K28609	21,94
gb10 - K40510	15,63	gb10 - K20050	9,05	gb10 - K28360	20,54	gb10 - K28610	11,06
gb11 - K40511	7,51	gb11 - K20051	4,31	gb11 - K28367	9,47	gb11 - H28611	4,34
gb12 - K40512	20,40	gb12 - K20012	2,67	gb12 - K28368	4,40	gb12 - H28632	3,57

*The information contained on page no 1-2 of this certificate is hereby certified to be correct statement of the tests and investigations carried out by ege testlaboratory on the material referred to.*

Signed by



Dorthe Daa Pedersen  
Laboratory Technician

Reported By



Henrik Schmidt Hansen  
Group CSR Director