



TEST REPORT

DATE: 03-17-2017

Page 1 of 1

TEST NUMBER: 0235297

CLIENT	Egetaepper a/s
---------------	----------------

TEST METHOD CONDUCTED	ASTM D5252 Standard Practice for the Operation of the Hexapod Tumble Drum Tester
------------------------------	--



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Rawline ECT350
CONSTRUCTION	Loop Pile
BACKING	Woven Synthetic

GENERAL PRINCIPLE

The test specimen is subjected to "Hexapod" tumbling in 2,000 cycle increments. A CRI/SOA upright vacuum was used to make four forward and backward passes along the length of the specimen after each 2,000 cycles.

After the specified total number of cycles is completed, the test specimen is visually assessed by three technicians for appearance change in accordance with the ASTM D7330 "Test Method for Assessment of Surface Appearance Change in Pile Floor Coverings Using Standard Reference Scales".

TEST RESULTS

NUMBER OF CYCLES	APPEARANCE RATING
12,000 – Heavy Ball	5.0

APPEARANCE RATING KEY	
5	Excellent: No visual change noticeable
4	Good: Slight change due to disturbance of pile
3	Fair: Noticeable change due to pile disturbance or matting
2	Poor: Loss of texture due to pile disturbance and/or matting
1	Very Poor: Severe pile disturbance and/or matting

APPROVED BY: 



This facility is accredited by the National Voluntary Laboratory Program for the specific scope of accreditation under lab code 100297-0. This accreditation does not constitute endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.