



Ege Carpets A/S  
Industrivej Nord 25  
7400 Herning  
Denmark

**Your Reference**  
**Customer Number** 40201  
**Contact Person** Ormstrup Lenette  
**E-Mail** lo@egecarpets.com

Vienna / 29.08.2023 / guse

## Classification Report VN710 222076.5

### Application

Classification of burning behaviour according to EN 13501-1.

### Test Material

WO-LWT

The test material used for testing was made anonymous for laboratory purposes.  
A detailed sample list is included in the document.

### Issuing

Original Issuing, 29.08.2023

Number Of Included Pages: 7

**OETI - Institut fuer Oekologie, Technik und Innovation GmbH**

A handwritten signature in blue ink, appearing to read 'Günther Sereinig'.

**Günther Sereinig**

Customer Service Officer



## 1 Application

Date of Order	Scope of Order
11.07.2023	Classification Of Burning Behaviour - EN 13501-1 (2018-12)

## 2 Introduction

This classification report defines the classification assigned to the building product group **WO-LWT** in accordance with the test methods fixed in EN 13501-1.

## 3 Details of classified building product

### 3.1 General

The building product group **WO-LWT** is defined as flooring, the classification is valid for the end use application described under point 5.3.

### 3.2 Description of the building product

The building product group **WO-LWT** is defined according EN 14041 as following.

Type	Textile floor covering with pile according to EN 1307
Dimensions	Rolls
Manufacturing technique	Tufted
Surface structure	Cut pile
Pile material	100% Wool
Total weight	1750 - 2650 g/m <sup>2</sup>
Total thickness	8,0 mm
Pile weight	1100 - 2000 g/m <sup>2</sup>
Pile thickness	6,0 mm

The applicant of this classification report guarantees the observance of the instructions for building product groups according EN 14041 as well as the observance of the instructions of the product specification according to EN 1307.

The following articles are part of the building product group **WO-LWT**

Article	Surface Structure	Manu- facturing technique	Total weight [g/m <sup>2</sup> ]	Total thickness [mm]	Pile weight [g/m <sup>2</sup> ]	Pile thickness [mm]
Graphic Wool 1100 LWT	Cut	Tufted	1 750	8,0	1 100	6,0
Graphic Wool 1200 LWT	Cut	Tufted	1850	8,0	1200	6,0
Graphic Wool 1300 LWT	Cut	Tufted	1950	8,0	1300	6,0
Graphic Wool 1400 LWT	Cut	Tufted	2050	8,0	1400	6,0
Graphic Wool 1500 LWT	Cut	Tufted	2150	8,0	1500	6,0
Graphic Wool 1600 LWT	Cut	Tufted	2250	8,0	1600	6,0
Graphic Wool 1700 LWT	Cut	Tufted	2350	8,0	1700	6,0
Graphic Wool 1800 LWT	Cut	Tufted	2450	8,0	1800	6,0
Graphic Wool 1900 LWT	Cut	Tufted	2550	8,0	1900	6,0
Graphic Wool 2000 LWT	Cut	Tufted	2 650	8,0	2 000	6,0

#### 4 Test reports and test results for the proof of the classification

For building product groups preliminary trials with the heaviest/thickest and lightest/thinnest quality have to be carried out (for the most unfavourable case a complete test has to be carried out) respectively the test results of these "border-qualities" are used for the judgement. The classification is done according to the worst case ("Graphic Wool 1100 LWT").

##### 4.1 Test report

Laboratory	OETI
Article	"Graphic Wool 1100 LWT"
Test report number	VN710 222076.1
Date of issue	03.07.2023
Applicant	Egetaepper A/S
Test methods	EN ISO 9239-1 and EN ISO 11925-2

## 4.2 Test results

	Test results (Mean Value)	Number of tests
<b>Ignitability, EN ISO 11925-2</b>		
Flame spread $\leq$ 150 mm	<b>yes</b>	6
<b>Burning behaviour, EN ISO 9239-1</b>		
Critical radiant flux	<b>7,7 kW/m<sup>2</sup></b>	3
Integral of smoke obscuration	<b>52 %.</b>	3

## 5 Classification and field of application

### 5.1 Reference for classification

This classification has been carried out in accordance with EN 13501-1.

### 5.2 Classification

Due to the results of the tests carried out, the building product group **WO-LWT** can be classified as following.

<b>Burning behaviour</b>	<b>Smoke emission</b>
<b>C<sub>fl</sub></b>	<b>s1</b>
<b>Classification</b>	
<b>C<sub>fl</sub>-s1</b>	

### 5.3 Field of application

The classification is valid for the building product group described in point 3 under the following end use conditions.

Application	Horizontal laid floor covering in form of rolls
Subfloors	Not burnable subfloors of euroclass A1 <sub>fl</sub> or A2 <sub>fl</sub> with a density of at least 1350 kg/m <sup>3</sup> .
Installation	glued
Adhesive	Polyacrylat-copolymer dispersion adhesive ("ege 90RH") or similar. Note: According to EN13501-1 the stated classification is valid for the tested floor covering together with the tested adhesive, as well as for all other adhesives of the same generic type as the tested adhesive.

## 6 Limitations

### 6.1 Notice

This classification document does not represent type permission or certifying the product.

If a building product should be CE marked according to system 3 of the attestation of conformity systems, the classification stated with this report is suitable as a basis for the declaration of the producer according to the attestation of conformity system 3, together with a CE marking in the context of the directive relating to construction products.

If the manufacturer plans a CE marking in connection with conformity system 3, he has to give an explanation, which has to be attached to the relevant documents. This explanation confirms, that there are no the specific materials, production processes or procedures (e.g. no additives of flame retarding materials, delimitation of organic components or additions of fillers), which are improving the burning behaviour to reach the obtained fire classification. As a consequence from this, the manufacturer drew the conclusion that the system 3 of the attestation of conformity systems is appropriate.

The testing laboratory therefore has played no role in the sampling procedure, although the testing laboratory keeps appropriate references from the manufacturer ready, in order to pursue the examined samples.



**Samples** Unless otherwise stated samples are provided by the customer. **Photo Overview** **Photo Overview** **Information Provided By The Applicant** **Preliminary Note** **Preliminary Note** For the requested article group and the submitted sample material, the application form provided for this as well as the legally binding signed declaration of commitment and conformity were handed over. **Sample Preparation**

## 7 Remarks

### Period of Validity

There are no regulations concerning duration of validity in the individual test standards. As the results of the examinations refer only to the submitted and examined samples, the report is valid for these for an unlimited period. A period of validity specified as part of an expert evaluation is in the discretion of the consultant or OETI. The applicability of results and expert evaluations for materials not tested is in the responsibility of the applicant. Whereby an apportionment of results as well as any specified period of validity can only be done for identically constructed products and only as long as the product is produced unchanged. Possible national or international restrictions concerning the terms of usability of test and classification reports have to be considered; this is not the responsibility of the test laboratory.

### Sample Material

Results of performed tests only refer to the sample material provided. The testing period is defined as timeframe between receipt of samples and issue date of test report. Without explicit written other agreement testing is destructive and the sample material is transferred to the property of OETI, which is entitled to freely decide on storage and disposal.

### Issuing

This test report is only issued as a PDF. Translations will be marked accordingly on the cover sheet.

### Quality Management, Accreditation And Notification

All tests and services are performed under a quality management system according to EN ISO/IEC 17025. OETI is accredited as Testing Laboratory and Certification Body for products. It also is a Notified Body (NB0534). (see <http://ec.europa.eu/enterprise/newapproach/nando/>). Accreditation was provided by Akkreditierung Austria. The scope of accreditation is listed on [www.oeti.biz](http://www.oeti.biz). Due to the system for the mutual recognition of national accreditations (ILAC/IAF), this accreditation is valid worldwide.

Statements of conformity are based on the specifications of the specified standard. The "simple acceptance rule" applies, that means the measurement uncertainty is stated for the statement of conformity, but not taken into account.

In this report individual non-accredited test procedures are marked with \*. Nevertheless, the analysis was also carried out for these parameters at the same level of quality as for the accredited parameters. The accreditation marking refers to the time of the first issuance of the report.

According to the decree on the use of the accreditation mark ("AkkZV") the accredited Conformity Assessment Body is the only one to use the accreditation mark. Application of the registration number of the Notified Body: As to personal protective equipment (PPE) the requirements of Regulation (EU) 2016/425 have to be kept. With construction products the application is only permitted within the declaration of performance for CE-marking.

### Copyright And Usage Notes

It is pointed out, that any alterations, amendments or falsifications of reports not authorized by the issuer of the report will be prosecuted as civil and criminal offences; this especially to the appropriate requirements of ABGB, UrhG, UWG and criminal law and their respective international equivalents. Reports are protected under international copyright laws. Written consent of the OETI GmbH is required for publications (also in excerpt) and reference to tests for public relation purposes. Reports may only be reproduced in full length.



End of Report